

ROKU® Glue T-NV, T-MV, T-HV

Material of building material classification A1 (non flammable) according to DIN 4102-1

General test certificate P-3104/2193-MPA BS

Product Description

ROKU® glue T-NV, T-MV and T-HV are low-viscous to high-viscous glues based on a watery sodium silicate solution with inorganic pigments. After hardening, the glues achieve extremely high thermal resistances up to +800 °C.

Application Areas

- Metals such as steel, aluminium and stainless steel sheets
- Gluing of mineral fibre, plaster or fibre silicate slabs
- Mineral and rock wool
- As glue for surfaces in door and element construction
- Plaster processing

Technical Data

Composition:	Glue on water glass basis
Material structure:	ROKU® glue T-NV: Low-viscous (thin) glue ROKU® glue T-MV: Medium-viscous (semi-fluid) glue ROKU® glue T-HV: High-viscous (thick) glue
Raw density [kg/m ³]:	1550 to 1630
Start of reaction [°C]:	From ca. 160
pH-value:	11,4 to 12



Supplied Forms

ROKU® glue T-NV:	15 kg container
ROKU® glue T-MV:	Upon request
ROKU® glue T-HV:	15 kg container

Please read the safety data sheet!

Processing and Storage

Processing:	Stir to glue to form a homogenous mass before processing. Use a spatula or suitable devices (e.g. spraying device for T-NV) to apply
Storage:	Store in a dry place between +8 °C and +25 °C; original, closed containers can be stored ca. 12 months after date of filling

*Ensure that surfaces are free from dust, fat or oil! Close opened containers air-tight and use as fast as possible!
Protect from frost or heat!*

Note

The information in this brochure is based on our knowledge and experience to date. This information does not release the user from carrying out independent tests and trials due to the various influences when processing and applying our product. It is not possible to derive a guarantee of certain properties or suitability of the product in a concrete application case based on our information. All the descriptions, drawings, photographs, data, conditions, weights etc. included may change without previous announcement; they do not constitute the contractually agreed property of the product. The recipient of our product is responsible to observe any trade mark rights and existing laws and regulations.
Corresponds to DIN 2304.