

Expiring product name: ROKU® Strip L 110

KERAFIX® Flexpan 200

Classification E (normal flammability) according to DIN EN 13501-1

European technical approval ETA-12/0152

Product Description

KERAFIX® Flexpan 200 is a stable, intumescent material on the basis of exfoliated graphite that foams up under pressure with thermal influence. Special features:

Reliable construction material with excellent properties in standard applications.

Application Areas

- Fire protection doors from steel or aluminium
- Special application areas of fire protection doors, e.g. box staples insulations and hinges
- Safety cabinets, control cabinets
- In drywall construction: Inspection flaps, separating walls and ceiling constructions
- Double floors

Technical Data

Composition:	Halogen free, foaming construction material on the basis of foaming graphite
Material structure:	Firm, flexible roll material
Raw density [kg/m ³]:	Ca. 1100
Start of reaction [°C]:	From ca. 170
Foaming rate [x-times]:	14 to 28 times (450 °C; 30 min; without load)
Direction of action:	Three-dimensional
Forming inflatable body:	Soft, coherent material
Foaming pressure [N/mm ²]:	At least 0,4
Thermal conductivity [W/mK]:	0,955

Executed Variants

KERAFIX® Flexpan 200 without additional lamination

Variant SK:	One-sided adhesive
Variant DF:	One-sided laminated with PVC-foil in different colors

Further variants on request.

Standard colours for ceiling foils and sheeting: Red, black and white; more colours upon request.

All variants – cut formats or formed parts (according to DIN 7715-5) may be equipped with various adhesive tapes.

Supplied Forms

Standard lengths:	25000 mm and 50000 mm
Widths:	Up to 320 mm
Thicknesses:	1,5 mm and 2 mm (Special thicknesses available on request)

Special formats are available on request. The product is manufactured on the basis of the general tolerance DIN ISO 2768-1. Please observe othe safety data sheet!

Note

The information in this brochure is based on our knowledge and experience to date. This information does not release the user from carrying out independent tests and trials due to the various influences when processing and applying our product. It is not possible to derive a guarantee of certain properties or suitability of the product in a concrete application case based on our information. All the descriptions, drawings, photographs, data, conditions, weights etc. included may change without previous announcement; they do not constitute the contractually agreed property of the product. The recipient of our product is responsible to observe any trade mark rights and existing laws and regulations. Adhesive bonds are to be applied according to DIN 2304.

